



This listing of claims will replace all prior versions, and listings, of claims in the application:

Listing of Claims:

1. (Original) A hindered amine compound represented by the general formula (I) or (II):




(in the formula, R is an alkyl group or a hydroxyalkyl group having 1-30 carbon atoms, or an alkenyl group having 2-30 carbon atoms, and n is an integer from 1-6. When n=1, R¹ is an alkyl group having 1-22 carbon atoms, an alkenyl group having 2-22 carbon atoms, or the group represented by the following general formula (III):




(R is the same alkyl group or hydroxyalkyl group having 1-30 carbon atoms, or alkenyl group having 2-30 carbon atoms as R above).

When n=2-6, R¹ is an organic group having 2-20 carbon atoms of valency n.



(in the formula, R is an alkyl group having 1-30 carbon atoms or an alkenyl group having 2-30 carbon atoms, R^2 is a hydrogen atom, an alkyl group having 1-22 carbon atoms or an alkenyl group having 2-22 carbon atoms, and A is a single bond, linear- or branched-alkylene group having 1-12 carbon atoms, alkylene group with ether linkage; n is an integer from 2-6; X is $-\text{C}(=\text{O})-$, a linear- or branched-alkylene group having 4-40 carbon atoms with a terminal $-\text{C}(=\text{O})\text{O}-$, a linear- or branched-alkylene group having 4-40 carbon atoms with a carbonic acid ester linkage, or an organic group having 6-30 carbon atoms with 3-6 terminal $-\text{O}-\text{C}(=\text{O})-$).

2. (Original) The hindered amine compound according to claim 1, wherein R in the general formula (I) is an alkyl group having 4-22 carbon atoms, n is 2, and R^1 is an alkylene group having 2-12 carbon atoms.
3. (Original) The hindered amine compound according to claim 1, wherein n in the general formula (I) is 1, and R is a group having the following general formula (III):



(R is an alkyl group having 10-22 carbon atoms).

4. (Currently Amended) A synthetic resin composition, wherein 0.01 to 10 weight parts of the hindered amine compound according to ~~any of claims 1 to 3~~ Claim 1, is blended with 100 weight parts of a synthetic resin.

5. (Currently Amended) A polyolefin resin composition, wherein 0.05-5 weight parts of the hindered amine compound according to ~~any of claims 1 to 3~~ Claim 1 is blended with 100 weight parts of a polyolefin resin.
6. (Original) An agricultural polyolefin film comprising the polyolefin resin composition according to claim 5.
7. (Currently Amended) A coating composition stabilized by the hindered amine compound according to ~~any of claims 1-3~~ Claim 1.
8. (Currently Amended) A synthetic resin composition, wherein 1-30 weight parts of one or more of melamine phosphate, melamine pyrophosphate, melamine polyphosphate, piperazine phosphate, piperazine pyrophosphate and piperazine polyphosphate as a flame retarder, and 0.01 to 10 weight parts of the hindered amine compound according to ~~any of claims 1 to 3~~ Claim 1, is blended with 100 weight parts of a synthetic resin composition.